



Dyckerhoff PZ Dreifach

Portland Cement EN 197-1 - CEM I 52,5 R

Data according to EN 196

	Typical data	Requirements in EN 197-1
Mechanical data:		
Compressive strength 2 days [MPa]	45	≥ 30,0
Compressive strength 28 days [MPa]	69	≥ 52,5
Physical data:		
Water demand [%]	30	
Setting time (initial) [min]	129	≥ 45
Le Chatelier test [mm]	1	≤ 10
Chemical data:		
Loss on ignition [%]	2,2	≤ 5,0
Insoluble residue [%]	0,7	≤ 5,0
Sulfate content (SO ₃) [%]	3,6	≤ 4,0

CEM I 52,5 R is produced, tested and certified acc. EN 197-1.

Certificate of consistency of performance: 0840-CPR-1270-110000-01

KOMO Certificate: 1140-16-1022

Dyckerhoff GmbH, Plant Lengerich
Postbox 1240 / 1260
D-49525 Lengerich
Phone: +49 (0)5481 / 31-0

Date: 07.01.2019
Dr. Böttcher (Quality assurance manager)